



# SPRAY/BASE & STAMP MIX

**PRODUCT DESCRIPTION:** The SS Spray/Base and Stamp Mix is a special blend of Portland cement and quality graded aggregates used to produce decorative treatments to properly prepared substrates. The SS Spray/Base mix is used for spray knockdown and troweled overlays and as a base coat for the Stamp Mix.

**SURFACE PREPARATIONS:** Apply to concrete at least 7 days old. Profile the surface to have a Concrete Surface Prep 1 rating in accordance to International Concrete Repair Institute (ICRI) standards. All contaminants must be removed from the host substrate including acid, residue, paint, oil, grease, sealers, wax and dirt, etc.

**DIRECTIONS FOR SPRAY/BASE:** Dilute three parts clean water to one part SS Polymer (3:1). This becomes the mix solution. Add the contents of the SS Spray/Base bag to 1.25 to 2 gallons of solution. Mix thoroughly with paddle drill or mortar mixer. Add pigment as needed, mix completely; apply SS Spray/Base Mix to properly prepared substrate dampened with a mix solution of 3:1. *Note:* Hopper gun applications such as knockdown and bubble finishes do not require a dampened substrate.

**DIRECTIONS FOR STAMP MIX:** Stamped overlays require one Base Coats and one Stamp Coat. Add the SS Stamp Mix bag to 1½ to 2 gallons of solution made up of 3 parts clean potable water to one part SS Polymer (3:1). Mix thoroughly with paddle drill or mortar mixer. Apply the Stamp Coat while the 2<sup>nd</sup> Base Coat is still wet. *Note:* Overworking the surface may cause loss of bond and air blisters. Cover with 1 mil poly after stamping to prevent surface cracking when applying in temperatures above 80°F or in full sun and high winds.

**LIMITATIONS:** The SS Spray/Base & Stamp Mix requires properly prepared cementitious substrates that are well drained and structurally sound. Loose concrete must be removed and ground water diverted from the host surface. *Note:* Application of surfaces with loose, deteriorated concrete or with coatings that may subsequently loosen are not suitable hosts for overlay products.



Distributed by Cimarron Wholesale | 125 NE 40th Street  
Oklahoma City, OK 73105 | Phone 866-906-2006 / Fax 405-526-2008

**COVERAGE RATES:**

SS Base/Spray Mix at 2:1 ..... 300—150 sq. ft.  
SS Stamp Mix at 3:1 ..... 26 sq. ft. at 1/4", 17 sq. ft. at 3/8", 13 sq. ft. at 1/2"  
SS Polymer 5 gallons = 10 bags SS Base/Spray Mix  
SS Polymer 5 gallons = 12 to 16 bags SS Stamp Mix

**TECHNICAL INFORMATION**

Physical Characteristics of SS Polymer  
Appearance ..... White Liquid  
Nonvolatile Content, % ..... 47(-) 0.5  
pH ..... 10.5-11.5  
Solids, % ..... 48%  
Bulk Density ..... 8.2 lbs/gallon  
Freeze Point ..... 32°F  
Glass Transition Temperature .... +12C

**PRECAUTIONS**

Keep out of reach of children!  
Do NOT allow polymer to freeze

**PACKAGING:** SS Spray/Base & Stamp Mix is packaged in 50 lbs bags.

**SPECIAL NOTES:** Please consult Material Safety Data Sheet (MSDS) and read Warranty information prior to use. This information can be requested by contacting customer service at 866-906-2006.